

## HUITEX HDPE ENHANCED SMOOTH GEOMEMBRANE - CONDUCTIVE

Properties	Test Method	HD/HP100	HD/HP150	HD/HP200	HD250
Thickness, mm					
Average values	ASTM D5199	1.00	1.50	2.00	2.50
Lowest Individual Reading		0.90	1.35	1.80	2.25
Sheet density, g/cm <sup>3</sup>	ASTM D792	0.940	0.940	0.940	0.940
Melt Index, 190/2.16, g/10min	ASTM D1238	<1	<1	<1	<1
Tensile Properties: <sup>(1)</sup>	ASTM D6693 Type IV specimen				
1.Strength at Yield, kN/m	@ 50 mm/min	15	22	29	37
2.Strength at Break, kN/m		27	40	53	67
3.Elongation at Yield, %	G.L. = 33 mm	12	12	12	12
4.Elongation at Break, %	G.L. = 50 mm	700	700	700	700
Tear Resistance, N	ASTM D1004	125	187	249	311
Puncture Resistance, N	ASTM D4833	320	480	640	800
Stress Crack Resistance, hrs	ASTM D5397 (Appendix)	500	500	500	500
Carbon Black Content, <sup>(2)</sup>	ASTM D1603	2-3	2-3	2-3	2-3
Carbon Black Dispersion	ASTM D5596	note(3)	note(3)	note(3)	note(3)
Oxidative Induction Time, mins					
- Standard OIT	ASTM D3895	100	100	100	100
- High Pressure OIT	ASTM D5885	400	400	400	400
Oven Aging at 85°C					
- Standard OIT, %	ASTM D5721	55	55	55	55
- High Pressure OIT	ASTM D3895	80	80	80	80
UV resistance	ASTM D7238				
High Pressure OIT, %	ASTM D5885	50	50	50	50
Roll Width, m		7/8	7/8	7/8	7
Roll Length, m		210	140	105	84
Roll Area, m <sup>2</sup>		1470/1680	980/1120	735/840	588

### NOTES:

(1). Machine direction (MD) and cross machine direction (XMD) average values should be on basis of 5 test specimens each direction.

Yield elongation is calculated using a gauge length of 33 mm.

Break elongation is calculated using a gauge length of 50 mm.

(2). The carbon black content of conductive layer will be higher than 3%.

(3). Carbon black dispersion for 10 different views: all 10 in Categories 1 or 2.

- All values are nominal test results, except as minimum or maximum when specified.

This specification is intended as guides only and is not intended as a warranty or guarantee. HuiKwang Corporation assumes no liability in connection with the use of this information. HuiKwang Corporation reserves the right to change the specification contained herein without notice.

Ver.12.2022