

HUITEX HDPE SINGLE SIDE TEXTURED GEOMEMBRANE – GM13

Properties	Test Method	HS075	HS100	HS150	HS200	HS250
Nominal Thickness, mm (1)		0.75	1.00	1.50	2.00	2.50
Average values	ASTM D5994	0.71	0.95	1.43	1.90	2.38
Lowest Individual Reading		0.64	0.85	1.28	1.70	2.13
Asperity Height (2)	ASTM D7466	0.40	0.40	0.40	0.40	0.40
Sheet density, g/cm ³	ASTM D792	0.94	0.94	0.94	0.94	0.94
Melt Index, 190/2.16, g/10min	ASTM D1238	<1	<1	<1	<1	<1
Tensile Properties:	ASTM D6693 Type IV specimen					
1.Strength at Yield, kN/m	@ 50 mm/min	11	15	22	29	37
2.Strength at Break, kN/m		8	10	16	21	26
3.Elongation at Yield, %	G.L. = 33 mm	12	12	12	12	12
4.Elongation at Break, %	G.L. = 50 mm	100	100	100	100	100
Tear Resistance, N	ASTM D1004	93	125	187	249	311
Puncture Resistance, N	ASTM D4833	200	267	400	534	667
Stress Crack Resistance, hrs	ASTM D5397 (Appendix)	500	500	500	500	500
Carbon Black Content, %	ASTM D1603	2-3	2-3	2-3	2-3	2-3
Carbon Black Dispersion	ASTM D5596	note(3)	note(3)	note(3)	note(3)	note(3)
Oxidative Induction Time, mins	ASTM D3895	100	100	100	100	100
Oven Aging at 85°C	ASTM D5721	55	55	55	55	55
Standard OIT, %	ASTM D3895					
UV resistance	ASTM D7238	50	50	50	50	50
High Pressure OIT, %	ASTM D5885					
Roll Width, m		8	8	8	8	7
Roll Length, m		225	170	128	98	76
Roll Area, m ²		1800	1360	1024	784	532

NOTES:

- (1). Lowest thickness for 8 out of 10 values is -10% of the nominal value; lowest thickness for any of the 10 value is -15% of the nominal thickness.
 - (2). Alternate the measurement side for double side textured sheet.
 - (3). Carbon black dispersion for 10 different views: all 10 in Categories 1 or 2.
- All values are nominal test results, except as minimum or maximum when specified.

This specification is intended as guides only and is not intended as a warranty or guarantee. Huikwang Corporation assumes no liability in connection with the use of this information. Huikwang Corporation reserves the right to change the specification contained herein without notice.

Ver.12:2022